

AMENDMENTS TO THE CLAIMS

Claim 1 (Currently Amended): A hydraulic transfer film comprising:

a substrate film containing a water-soluble or water-swellaable resin;

a transfer layer which is hydrophobic and soluble in an organic solvent provided on the substrate film; and

a peelable film which can be peeled off at the interface with the transfer layer provided on the transfer layer, wherein

the transfer layer contains a curable resin layer which contains a curable resin selected from the group consisting of a radiation-curable resin having at least three (meth)acryloyl groups in a molecule, and a thermosetting resin containing blocked isocyanate and polyol[[],] ; and also contains a non-polymerizable thermoplastic resin having a glass transition temperature of 35 to 200°C which is compatible with the curable resin.

Claim 2 (Original): The hydraulic transfer film according to claim 1, wherein the transfer layer comprises a curable resin layer provided on the substrate film and a decorative layer having a printing ink film or a coating film provided on the curable resin layer.

Claim 3 (Currently Amended): The hydraulic transfer film according to claim 1 or 2, which is produced by laying a film (I) comprising a hydrophobic curable resin layer which is curable by at least one of irradiation with radiation and heating and is soluble in an organic solvent provided on the substrate film containing a water-soluble or water-swellaable resin, and a film (II) comprising a decorative layer made of a printing ink film or a coating film which is hydrophobic and soluble in an organic solvent provided on the peelable film one upon another so that the curable resin layer of the film (I) and the decorative layer of the film (II) face each other, and laminating them by dry lamination.

Claim 4 (Currently Amended): The hydraulic transfer film according to claim 3, wherein the film ~~(I)~~ (I) comprising the curable resin layer provided the substrate film is made of polyvinyl alcohol and the temperature on heat lamination with the film (II) comprising the decorative layer provided on the peelable film is from 40 to 120°C.

Claim 5 (Previously Presented): The hydraulic transfer film according to claim 1, wherein an adhesion initiation temperature of the curable resin layer is 40°C or higher and 120°C or lower.

Claim 6 (Canceled)

Claim 7 (Previously Presented): The hydraulic transfer film according to claim 5, wherein the curable resin layer contains a radiation-curable resin having a mass-average molecular weight of 300 to 10,000 and having at least three (meth)acryloyl groups in a molecule, and a non-polymerizable thermoplastic resin having a mass-average molecular weight of 10,000 to 400,000 and Tg of 35 to 200°C.

Claim 8 (Previously Presented): The hydraulic transfer film according to claim 5, wherein the curable resin layer contains a radiation-curable resin selected from the group consisting of (1) polyurethane (meth)acrylate having at least three (meth)acryloyl groups in a molecule, (2) polyester (meth)acrylate having at least three (meth)acryloyl groups in a molecule, and (3) epoxy (meth)acrylate having at least three (meth)acryloyl groups in a molecule and the non-polymerizable thermoplastic resin which is polymethacrylate.

Claim 9 (Previously Presented): The hydraulic transfer film according to claim 5, wherein the curable resin layer contains blocked isocyanate and polyol.

Claim 10 (Previously Presented): The hydraulic transfer film according to claim 9, wherein the curable resin layer contains polyol having a mass-average molecular weight of 3,000 to 100,000 as a base agent and blocked isocyanate as a curing agent.

Claim 11 (Canceled)